Drawn Arc Stud Welder

Advantages

- Excellent reliability
- Uniform high welding quality
- No additional material such as flux or filler necessary
- High duty cycle
- Elimination of operations such as drilling and rivetting



Drawn Arc Stud Welder



Drawn arc stud welding is an extremely efficient method of attaching fasteners primarily to mild steel and stainless steel by utilizing a constant current DC power supply. In this welding process, a welding rectifier serves as an energy source and provides a continuous welding current. The welding time can be adjusted from 10 to 500 milliseconds. When a weld is initiated, current begins to flow through the stud while the weld gun simultaneously lifts the stud to draw an arc, which melts the base of the stud and adjoining surface on the workpiece. Upon completion of the weld time, the gun plunges the stud back to the workpiece, resulting in a permanent bond as the molten material solidifies. The whole process takes less than one second.

During the welding process, a welding fillet is formed around the base of the stud, the dimension of which is predetermined by the ceramic ferrule. The ceramic ferrule concentrates the welding arc and forms a weld fillet around the stud base. Weld gun with shielding gas option can also be used.

This method has a higher depth of penetration compared to other stud welding processes. These machines are most commonly used in transformer manufacturing, ship building industry, boiler industry, power plants, automobile industry etc.

Technical Data AR 5000

Stud Welding Range	M4 to M12
Welding Current	800 Amps. Max
Welding Time	10 to 500ms
Power	415V 3 phase 50Hz
Power Source	Transformer / Rectifier
Welding Cable	3 Meter
Welding Material	Mild Steel, Stainless Steel
Welding Gun	Gap Gun

Specifications subject to change without notice

- Password protection
- Alpha-numeric text display
- · Fine adjustment of weld time
- Weld counter
- Protection against overloading of machine





ARTECH WELDERS PVT. LTD.

A-16, H-Block, M.I.D.C., Pimpri, Pune-411018, India. Tel:+91-20-27476160 • 27462771 / 72 Telefax:+91-20-27461348

E-mail: artech1@vsnl.com
Website: www.artechengg.com